

## ::: BESA URKI VOC LACQUER GLOSSY A+B

### *Description:*

2 component durable, high-build, slightly elastic PUR varnish for finishing wood, glass, plastic, metal and non-ferrous metals. Highly resistant to sun, water, chemicals and diluted acids and alkalis. Retains its high gloss and is UV-resistant. Is ideal to be sprayed with a spray gun.

Limited number of colours available in 750ml (A+B), according to ral colour in 5 lt and 20 lt packages (A-comp.)

### *Application:*

As a finishing coat for various applications to boat, construction and model making. Can be applied with a brush or a spray gun. For spraying, however, one should dilute by 15-20% with Urkisol 8229. For brush application we recommend to dilute 5-10%.

### *Data on delivery:*

	<u>A-Comp.</u>	<u>B-Comp.</u>
Color:	colourless / Ral colour	colourless
Viscosity:	800 mPas	800 mPas
Mass density:	approx. 1,38 gr/cm <sup>3</sup>	approx. 1.07 gr/cm <sup>3</sup>
Shelf life:	12 months in closed packaging	12 months in closed packaging
Consistency:	liquid	liquid

### *Technical data:*

Consumption:	9 -10 m <sup>2</sup> /liter
Shore:	not applicable

### *Processing:*

Always ensure a dry and grease-free surface. Never use in the full sun. Mix both components in a 2/1 volume ratio. Mix the individual components well before use. Allow the mixture to rest for approx. 15 min. and then process it within 3 hours. Waiting time between layers min. 3 hours. Dust dry after 1 hour, tack free after 4 hours. As extra adhesive layer for porous substrates you can use primer G4, for aluminium or stainless steel substrates you can use Epoxy Lightprimer. Spray pressure: 2,5-4 bar at an opening of 1,5-1,8 mm.

Attention: too much humidity can lead to the formation of air bubbles on the surface.

### *Safety:*

Always provide appropriate protective clothing and gloves. Avoid prolonged skin contact.

The use of a carbon filter mask type A2 is recommended.

Cleaning agent for tools: cleaner M (environmentally friendly substitute for acetone).