

::: SILICONE RUBBER KNEADABLE A+B

Description:

Is a 2-component kneadable, self-demoulding silicone that can be easily kneaded with the hands into a paste. Because of its rapid hardening, it is ideal for use on ceilings or moulds that are difficult to cast. Available in 200 gr, 1 kg, 10 kg and 40 kg packaging.

Application:

As a kneading compound for all kinds of impressions on cornices and ceiling elements. This silicone can be used on the skin for impressions or in the orthopaedic sector for making toe corrections.

Data on delivery:

| | <u>A-Comp</u> | <u>B-Comp</u> |
|---------------|------------------------------|------------------------------|
| Color: | white - grey | blue |
| Viscosity: | 40,000 MPa | 40,000 MPa 1.24 |
| Mass density: | 1,24 | 6 months in closed packaging |
| Shelf life: | 6 months in closed packaging | paste |
| Consistency: | paste | |

Technical data: (A + B)

Consumption: depending on application
Shore: A47

Processing:

Mix the two components in a 1/1 weight ratio to obtain a homogeneous mass. Mixing time: 1 minute. Processing time: 1 minute. Curing time: +-5 min. Caution: close pots well after use. Do not use too large quantities, as the processing time is short.

If you have any doubts about the substrate, it is best to make a test piece or to use release agent Trennspray.

Note: Latex gloves hinder the curing of the silicone material. It is therefore recommended to wear vinyl gloves and to wash your hands thoroughly.

Safety:

Always provide appropriate protective clothing and gloves. Cleaning agent for tools: cleaner M (environmentally friendly substitute for acetone).

The information on this page concerns technical instructions and has been compiled to the best of our knowledge. However, it shall not constitute grounds for any liability on our part.