

## ::: EPOXY SOLOMET A+B

### *Description:*

Is a 2-component solvent-free kneading compound on an epoxy basis. Can be handled like dough, becomes steel hard and also adheres to damp surfaces. Available in 57 g packages.

### *Application:*

As a repair paste for steel, cast iron, tin, copper, lead, aluminium, wood, concrete, ceramics, fibrocement and PVC. For sealing cracks and holes in fireplaces, boilers and pipes.

<i>Data on delivery:</i>	<u>A-Comp</u>	<u>B-Comp</u>
Color:	alu	alu
Viscosity:	20000 mPas	20000 mPas
Mass density:	approx. 1,60 gr/cm <sup>3</sup>	approx. 1,60 gr/cm <sup>3</sup>
Shelf life:	18 months in closed container	18 months in closed container
Consistency:	paste	paste

### *Technical data: (A + B)*

Consumption:	depending on application
Shore:	D : 80
Tensile strength	6.2 N/mm <sup>2</sup>

### *Processing:*

Mix both components in a 1/1 volume parts ratio. Potlife: 2-3 minutes dry within 5-10 minutes. Sandable after 8 hours. Processing temp. : 10-35°C. Hardened after 8-12 hours. Apply with hands. Temperature resistance permanently 120°C and max. 150°C.

Can even be applied under water.

### *Safety:*

Always provide appropriate protective clothing and gloves. Cleaning agent for tools: cleaner M (environmentally friendly substitute for acetone).