

**:: PUR H200-AT A-COMP.**

**Description:**

Is a 2-component structural polyurethane foam. Should always be used in combination with the B-component. After curing you get a very hard foam with a closed cell structure and skin formation with a density of 200 kg/m<sup>3</sup>. CFC-free floating agent. Resistant to chemicals and acids. Available in 1 kg, 10 kg and 200 kg packaging.

**Application:**

For filling hollow spaces or shapes. You can imitate wood with H 200 if you pour it into a silicone mould, for example. Also used in orthopaedics to make shoe lasts.  
For the manufacture of handles. Due to the closed cell structure, suitable for long-term contact with water. Can be painted, glued, filled, nailed and screwed. Can be coloured with 5% PUR pigment.  
Attention: does not give a homogenous colour.  
When exposed to sunlight, the material may discolour after a while.

**Data on delivery:**

Color:	colourless-yellow
Viscosity:	260 mPas
Mass density:	approx 1,09 gr/cm <sup>3</sup>
Shelf life:	6 months in closed packaging
Consistency:	liquid

**Technical data:**

Consumption:	200 kg/m <sup>3</sup>
Shore:	not applicable

**Processing:**

Mix both components in a 100/100 weight ratio and pour into the shape or area to be filled. The potlife is approx. 65 sec. The expansion is approx. 5 x the volume. Dry after 15 min.  
De-formable after 20 min. and fully cured after 12 hours. Make sure the processing temperature is between 20°C and 25°C. Store the foam between 10 and 25°C. Mixing is best done with a mechanical mixer. As a release agent we recommend APW.

**Safety:**

Always provide appropriate protective clothing and gloves. Avoid prolonged skin contact. The use of a carbon filter mask type A2 is recommended.

**Caution:** container may be under pressure.

Cleaning agent for tools: cleaner M (environmentally friendly substitute for acetone).