

:: EPOXY ANTI-CORROSION PRIMER A+B

Description:

Is a high-quality 2-component solvent-free epoxy primer based on amine. The hardened layer has a very high resistance and is a good barrier against water. The hardened layer does not allow water (vapour) to pass through.

Available in 750 ml and 7.50 lt packages.

Application:

The product is applied on hard surfaces as a protective layer against water, on polyester as an osmosis prevention and on metal as a protection against rust.

Data on delivery:

	<u>A-comp.</u>	<u>B-comp.</u>
Color:	red	amber
Viscosity:	> 20,5 cSt	n/a
Mass density:	approx. 1,55 gr/cm ³	approx. 0.93 gr/cm ³
Shelf life:	24 months in closed packaging	24 months in closed packaging
Consistency:	liquid	liquid

Technical data: (A + B)

Consumption:	approx. 11-12 m ² /lt
Shore:	not applicable

Processing:

Depending on the surface and quality, sandblast or sandpaper. The surface must be clean, dry and grease-free. Only use from 15°C. Mix both components in a 4/1 volume ratio and process within 2-3 hours. Apply with roller or brush. Hand-dry after 5 hours at 20°C. Sandable after 24 hours. Cured after 7 days. Can be repainted after minimum 5 hours and maximum 30 days. Apply 2-4 layers for an optimal sealing. If Seaguard fouling stop is applied afterwards, apply a layer of Light Primer first.

Before launching, the ANTICORROSION PRIMER should be left to harden for at least 7 days (20°C).

Safety:

Irritating to eyes. Always wear suitable protective clothing and gloves. Wearing a carbon filter mask is recommended. Keep out of reach of children. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. If swallowed, seek medical advice immediately and show this container or label. Not for large surface areas and living quarters. Cleaning agent for tools: thinner epoxy or cleaner M (environmentally friendly substitute for acetone).