

::: ESTOVOSS STANDARD GREY

Description:

Is a 1 component solvent-based PU resin that reacts to humidity. Satin gloss paint for garage floors, basements, work and hobby areas. Limited UV resistance. Available in 1 lt, 5 lt and 10 lt containers.

Application :

As waterproofing for porous substrates. Final coat for concrete, metal for inside.
In case of freshly poured concrete, wait at least 28 days before applying G4 Primer and then Estovoss. Easy to maintain. High-quality finish for basements and garages. Exists only in a grey colour +- Ral 7001.

Data on delivery:

Color:	grey
Viscosity:	250 mPas
Mass density:	approx. 1.5 g/cm ³
Shelf life:	6 months in closed packaging
Consistency:	liquid

Technical data:

Consumption:	300 gr/m ² /1st layer (=200 ml) + 200 gr/m ² /2nd layer (=130 ml)
Shore	not applicable

Processing:

Always ensure that the surface is as dry and grease-free as possible and apply our primer G4 with a brush or roller. After 2-4 hours (max. 12) Estovoss can be applied.

Apply Estovoss with a brush or roller. It is dust-dry after 2 hours. Waiting time between layers: 6 to 8 hours with a max. of 12 hours. Can be thinned with max. 10% PU thinner. Can be walked on after 6 hours, lightly loaded after 12 hours and fully hardened after 7 days. You can use our anti-slip granulate to make the surface anti-slip. Stir well before use. For further information, please consult our processing sheet.

Beware of opened containers; they must always be closed airtight to prevent further hardening in the tin. Pour any surplus into a smaller container. Should any skin formation occur, please remove it carefully.

Attention: too high a degree of humidity can lead to the formation of air bubbles on the surface.

Safety:

Always provide appropriate protective clothing and gloves. Avoid prolonged skin contact. The use of a carbon filter mask type A2 is recommended.

Cleaning agent for tools: cleaner M (environmentally friendly substitute for acetone)

Caution: is highly flammable.