

## :: PERFECT POOL FINISH CLEAR A+B

### *Description:*

2 component high performance finishing coat specially developed for recoating a swimming pool made of glass fibre reinforced polyester or concrete. It is available in satin gloss. Has an excellent coverage after application of a primer. Extremely resistant to sun, water, chemicals and diluted acids and lyes that are present in swimming pools. Available in 4 kg sets.

### *Application:*

As a finishing coat for mono-blocks and older pools consisting of glass fibre reinforced polyester. Used as an extra protective layer after renovating with the coloured Perfect Pool Finish. This ensures a better colour fastness, especially at water temperatures above 30 °C. Can be applied by brush or roller. This product is not used for protection against osmosis.

<i>Data on delivery:</i>	<u><i>A-Comp.</i></u>	<u><i>B-Comp.</i></u>
Color:	colourless	colourless
Viscosity:	800 mPas	800 mPas
Mass density:	approx. 1.15 gr/cm <sup>3</sup>	approx. 1.07 gr/cm <sup>3</sup>
Shelf life:	24 months in closed packaging	18 months in closed packaging
Consistency:	liquid	liquid

### *Technical data:*

Consumption: 6 -8 m<sup>2</sup>/litre  
Shore: not applicable

### *Processing:*

Always ensure a dry and grease-free surface. Do not apply the Perfect Pool Finish Clear Satin in full sunlight. Mix the individual components thoroughly beforehand. Afterwards, use a 1/1 weight ratio. Let this mixture rest for about 15 minutes and then process within 4 hours.

Waiting time between layers min. 12 hours and max. 48 hours, because this way it remains repaintable without intermediate sanding of the previous layer. Dust dry after 15 min. Tack free after 3 hours. Dry after 12 hours and fully hardened after 7 days.

Attention: too high a relative humidity can lead to the formation of air bubbles on the surface. The relative humidity may not exceed 85%, while the temperature of the surface during application must be at least 8°C and 3°C higher than the dew point.

### *Safety:*

Always provide appropriate protective clothing and gloves. Avoid prolonged skin contact. The use of a carbon filter mask type A2 is recommended.

Cleaning agent for tools: cleaner M (environmentally friendly substitute for acetone)

---

The information on this page concerns technical instructions and has been compiled to the best of our knowledge. However, it shall not constitute grounds for any liability on our part.